

DATA SHEET 22SPN.080.01015

## SPN

White glossy PP Face Film for the production of self-adhesive labels for ink jet label printers.

### Printing Systems



### Rolls

| Art.Number      | Width (mm) | Thickness | Length (m) |
|-----------------|------------|-----------|------------|
| 22SPN.080.01015 | 1015       | 0.060 mm  | bulk roll  |
| 22SPN.080.01020 | 1020       | 0.060 mm  | bulk roll  |
| 22SPN.080.01270 | 1270       | 0.060 mm  | bulk roll  |
| 22SPN.080.01530 | 1530       | 0.060 mm  | bulk roll  |

### Technical data

#### Characteristic

- High brilliance of colours
- High Level Ink Absorption
- Inkjet coating for the indirect food contact ISEGA / FDA-certified
- Tear resistant
- Very fast ink drying
- Good resistance to aceton, ethanol
- Good cut and die cut performance

#### Finish

- White glossy

## Specifications

|  |   |
|--|---|
| Coating Printside                              | nanoporous coating, boric acid content<br>max 0,1%  |
| Width (mm)                                     | 1015  |
| Thickness of carrier material                  | 0.060 mm  |
| Thickness base material with<br>inkjet coating | 0.086 mm +/- 0.010 mm   |
| Grammage                                       | Base film 45 g/m <sup>2</sup> +/- 3 g/m <sup>2</sup> , Coating<br>weight 26 g/m <sup>2</sup> +/- 7,5g/m <sup>2</sup>          |
| Length (m)                                     | bulk roll   |
| Roll width / Roll usable width                 | Please contact Folex if you need other roll<br>widths and roll lengths. We can convert the<br>rolls according to your wishes. |
| Base Material                                  | Polypropylene   |

## Compatibility

- Suitable for most Ink Jet label roll printers using dye- or pigmented inks.

## Storage

- Shelf life: 1 year after delivery
- In its original packing at 20-25°C, 45-55% humidity.

## Product liability clause

The foregoing information and any consulting provided by us in terms of application engineering shall be given to our best knowledge, but shall not be considered binding information neither with regard to any third party industrial property rights. Any such consulting shall not relieve you from your own review of our current consulting information as to their suitability for the intended procedures and applications. It is the users responsibility to determine the suitability for his/her own use and application and test through the complete production process to ensure the product is fully suitable for the intended use, since conditions of use are beyond our control. The sale of our products shall be subject to our current General Terms and Conditions. We reserve the right to make changes that serve to improve the product.